

9. 粘度调节剂

产品 **TAC-OIL BA**

特性 Tac-Oil BA 是一种高效，粘稠的增粘剂，由溶于菜籽油中的天然橡胶组成
Tac-Oil BA 的添加符合 RAL-UZ 178 / Annex 1 的环境标签，可用于可生物降解的润滑剂和液压油。

技术资料		典型	规格		
		数值	最小	最大	
密度 15°C (g/ml)	:		0.900	0.940	DIN 51 757
粘度 40°C (mPa·s)	:		20000	30000	DIN EN ISO 53 015
闪点 (°C)	:	min. 150			DIN EN ISO 2719
生物降解率	:	81%	28 days		OECD 301 B

应用 Tac-Oil BA 在润滑油或脂中的推荐含量为 1.0-5.0 wt. %。
特别是用于电锯，包装机械和防锈剂的润滑油需要增粘剂，以防止油飞溅或掉落。

Tac-Oil BA 装在 55 加仑油桶（净重 180 千克）中。可能会在 20°C 的 10-20 分钟内排光。在均质化之前，不得在润滑脂中添加粘性剂。通过缓慢运行的机械搅拌器，与油的混合最好在 60°C 至 80°C 之间进行。切勿使用高剪切搅拌器和泵。Tac-Oil BA 在有限的时间内可稳定在 80°C 的温度下。

存储 在干燥的非冻结储存条件下，Tac-Oil BA 可以在密封的原始包装中存放至少 9 个月。

The data contained herein serve as general information for our customers only and are not binding. The data contained herein have been collected to the best of our knowledge and do not constitute any advice or warranty to our customers for any specific application. It is up to our customer at their own risk to determine the suitability of each product for their individual purposes. The products are sold without any representation, warranty or guarantee either expressed or implied. Our liability is limited to the value of the supplied merchandise.